

## **Patent Abstracts of Japan**

PUBLICATION NUMBER : 10289813 PUBLICATION DATE : 27-10-98

APPLICATION DATE : 16-04-97 APPLICATION NUMBER : 09098613

APPLICANT: HITACHI METALS LTD;

INVENTOR: TANIGUCHI FUMITAKE;

INT.CL. : H01F 1/053 C22C 38/00

TITLE: RARE-EARTH MAGNET

ABSTRACT: PROBLEM TO BE SOLVED: To inhibit the oxidization of rare-earth elements being

contained in an R-T-B rare-earth magnet alloy and to reduce the B-rich phase of a rake-earth magnet while an increase in the coarseness of the  $R_2T_{14}B$  main phase of the magnet is suppressed by a method wherein the magnet has a composition consisting of R, B, Co, M, oxygen, nitrogen and carbon, which respectively have a specified wt.%, with the balance of Fe, the coersive force of the magnet at a specified temperature is specified

and at the same time, the area ratio of the B-rich phase is specified.

SOLUTION: A rare-earth magnet has a composition consisting of 27.0 to 31.0 wt.% of R (The R is one kind of the element or more than two kinds of the elements out of rare-earth elements including Y.), 0.8 to 1.02 wt.% of B, 0.5 to 50 wt.% of Co, 0.01 to 1.0 wt.% of M (The M is one kind of the element or more than two kinds of the elements out of Ga, Al and Cu), 0.25 wt.% or lower of oxygen, 0.02 to 0.15 wt.% of nitrogen and 0.15 wt.% or lower of carbon with the balance of Fe. Moreover, the coercive force of the magnet at  $20^{\circ}\text{C}$  is 13 kOe or higher and at the same time, the area ratio of the B-rich phase of the magnet is 0 to 0.5% and the area ratio of main phase crystal grains of a grain diameter of  $16\,\mu\text{m}$  or wider is 10% or lower.

COPYRIGHT: (C)1998,JPO